

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations Revision date: 11/11/2014 Supersedes:08/28/2014

SECTION 1: Identification of the subst	ance/mixture and of the company/undertaking
1.1. Product identifier	
	P150-32D PAG Refrigeration Lubricant 150 + U/V Dye
	P150-32D
1.2. Relevant identified uses of the substa	nce or mixture and uses advised against
Use of the substance/mixture	Polyalkylene Glycol based lubricant with ultraviolet leak detection dye to help detect leaks in air conditioning systems.
1.3. Details of the supplier of the safety da	ta sheet
Tire Seal, Inc. 3574 Corona Street 33461 Lake Worth, Florida - USA T 561-582-2245 - F 561-582-1499 www.supercool.ac	
1.4. Emergency telephone number	
Emergency number :	USA PHONE:1-800-373-7542, INT'L: 1-484-951-2432 DGA/AAG ENVIRONMENTAL CONTRACT: DGA4000-048
SECTION 2: Hazards identification	
2.1. Classification of the substance or mix	ture
Classification (GHS-US) Not classified	
2.2. Label elements	
GHS-US labeling	
No labeling applicable	
2.3. Other hazards	
No additional information available	
2.4. Unknown acute toxicity (GHS-US)	
No data available	
SECTION 3: Composition/information	on ingredients
3.1. Substance	
Not applicable	
Full text of H-phrases: see section 16	
3.2. Mixture	
SECTION 4: First aid measures	
4.1. Description of first aid measures	
First-aid measures general	Never give anything by mouth to an unconscious person. If you feel unwell, seek medical advice (show the label where possible).
First-aid measures after inhalation :	Assure fresh air breathing. Allow the victim to rest.
First-aid measures after skin contact	Remove affected clothing and wash all exposed skin area with mild soap and water, followed by warm water rinse.
First-aid measures after eye contact	Rinse immediately with plenty of water. Obtain medical attention if pain, blinking or redness persist.
First-aid measures after ingestion :	Rinse mouth. Do NOT induce vomiting. Obtain emergency medical attention.
4.2. Most important symptoms and effects	, both acute and delayed
Symptoms/injuries :	Not expected to present a significant hazard under anticipated conditions of normal use.
4.3. Indication of any immediate medical a	ttention and special treatment needed
No additional information available	
SECTION 5: Firefighting measures	
5.1. Extinguishing media	
Suitable extinguishing media	Foam. Dry powder. Carbon dioxide. Water spray. Sand.

Unsuitable extinguishing media : Do not use a heavy water stream.

Version: 2.1

Safety Data Sheet according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

5.2. Special hazards arising from the	substance or mixture
No additional information available	
5.3. Advice for firefighters	
Firefighting instructions	: Use water spray or fog for cooling exposed containers. Exercise caution when fighting any chemical fire. Prevent fire-fighting water from entering environment.
Protection during firefighting	: Do not enter fire area without proper protective equipment, including respiratory protection.
SECTION 6: Accidental release me	easures
6.1. Personal precautions, protective	equipment and emergency procedures
6.1.1. For non-emergency personnel	
Emergency procedures	: Evacuate unnecessary personnel.
6.1.2. For emergency responders	
Protective equipment	: Equip cleanup crew with proper protection.
Emergency procedures	: Ventilate area.
6.2. Environmental precautions	
Prevent entry to sewers and public waters. No	otify authorities if liquid enters sewers or public waters. Avoid release to the environment.
6.3. Methods and material for contain	ment and cleaning up
Methods for cleaning up	: Soak up spills with inert solids, such as clay or diatomaceous earth as soon as possible. Colle spillage. Store away from other materials.
6.4. Reference to other sections	
See Heading 8. Exposure controls and person	nal protection.
SECTION 7: Handling and storage	
7.1. Precautions for safe handling	
Precautions for safe handling	Wash hands and other exposed areas with mild soap and water before eating, drinking or smoking and when leaving work. Provide good ventilation in process area to prevent formation of vapor.
7.2. Conditions for safe storage, inclu	uding any incompatibilities
Storage conditions	: Keep container closed when not in use.
ncompatible products	: Strong bases. Strong acids.
ncompatible materials	: Sources of ignition. Direct sunlight.
7.3. Specific end use(s)	
No additional information available	
No additional information available	ersonal protection
No additional information available SECTION 8: Exposure controls/pe	ersonal protection
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters	ersonal protection
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0)	
No additional information available SECTION 8: Exposure controls/period 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/	
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls	A (mg/m ³) 2 mg/m ³
No additional information available SECTION 8: Exposure controls/period 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/	
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection	 A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limit
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Respiratory protection	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Cyner information	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cther information SECTION 9: Physical and chemica	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cther information SECTION 9: Physical and chemica a.1. Information on basic physical and	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cher information SECTION 9: Physical and chemica 9.1. Information on basic physical an Physical state	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use. al properties : Liquid
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cher information SECTION 9: Physical and chemica 9.1. Information on basic physical and Physical state Appearance	A (mg/m ³) 2 mg/m ³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use. Al properties d chemical properties : Liquid : Clear.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cyther information SECTION 9: Physical and chemica Discrete Appearance Color	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use. Al properties : Liquid : Clear. : Reddish Green Tint.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cother information SECTION 9: Physical and chemica 3.1. Information on basic physical an Physical state Appearance Color Ddor	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use. Al properties : Liquid : Clear. : Reddish Green Tint. : Characteristic.
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cther information SECTION 9: Physical and chemica Appearance Color Ddor Ddor Ddor threshold	A (mg/m³) 2 mg/m³ : Avoid all unnecessary exposure. : : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use. Al properties : Liquid : Clear. : Reddish Green Tint. : Characteristic. : No data available
No additional information available SECTION 8: Exposure controls/pe 3.1. Control parameters 2,6-di-tert-butyl-p-cresol (128-37-0) USA ACGIH ACGIH TW/ 3.2. Exposure controls Personal protective equipment Hand protection Eye protection Eye protection Cher information SECTION 9: Physical and chemica 9.1. Information on basic physical and Physical state Appearance Color Cdor Cdor Cdor Cdor Cdor Cdor Cdor Cd	A (mg/m ³) 2 mg/m ³ : Avoid all unnecessary exposure. : The use of gloves impervious to the specific material handled is advised to prevent skin contact. Suggested protective material: Nitrile, 4.5 mil thickness, tested at 3.5 ml and above with no breakthrough time after 240 minutes. : Chemical goggles or safety glasses. : Normally not required. Where there is potential for airborne exposure above the exposure limi an approved air purifying respirator equipped with Type R or P95 particle filters may be used. : Do not eat, drink or smoke during use. A properties d chemical properties : Liquid : Clear. : Reddish Green Tint. : Characteristic. : No data available : No data available

Safety Data Sheet according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

	-	
Freezing point	:	No data available
Boiling point	:	> 200 °C Calculated
Flash point	:	204 °C Closed Cup
Self ignition temperature	:	No data available
Decomposition temperature	:	No data available
Flammability (solid, gas)	:	No data available
Vapor pressure	:	No data available
Relative vapor density at 20 °C	:	No data available
Relative density	:	No data available
Solubility	:	No data available
Log Pow	:	No data available
Log Kow	:	No data available
Viscosity, kinematic	:	124 - 139 cSt @40ºC
Viscosity, dynamic	:	No data available
Explosive properties	:	No data available
Oxidizing properties	:	No data available
Explosive limits	:	No data available

9.2. **Other information**

No additional information available

0505			
SECT	ION 10: Stability and reactivity		
10.1.	Reactivity		
No additional information available			
10.2.	Chemical stability		
Not esta	ablished.		
10.3.	Possibility of hazardous reactions		
Not esta	ablished.		
10.4.	Conditions to avoid		
Direct s	unlight. Extremely high or low temperatures.		
10.5.	Incompatible materials		
Strong acids. Strong bases.			
10.6.	Hazardous decomposition products		

Carbon monoxide. Carbon dioxide.

SECTION 11: Toxicological information	
--	--

11.1. Information on toxicological effects	
Acute toxicity	: Not classified
2,6-di-tert-butyl-p-cresol (128-37-0)	
LD50 oral rat	890 mg/kg (Rat; OECD 401: Acute Oral Toxicity; Experimental value; >6000 mg/kg bodyweight; Rat)
LD50 dermal rat	> 2000 mg/kg (Rat; Literature study; OECD 402: Acute Dermal Toxicity; >2000 mg/kg bodyweight; Rat; Experimental value)
ATE (oral)	890.000 mg/kg body weight
Skin corrosion/irritation	: Not classified
Serious eye damage/irritation	: Not classified
Respiratory or skin sensitization	: Not classified
Germ cell mutagenicity	: Based on available data, the classification criteria are not met
Carcinogenicity	: Not classified
2,6-di-tert-butyl-p-cresol (128-37-0)	
IARC group	3
Reproductive toxicity	: Based on available data, the classification criteria are not met
Specific target organ toxicity (single exposure)	: Not classified
Specific target organ toxicity (repeated exposure)	: Based on available data, the classification criteria are not met
Aspiration hazard	: Based on available data, the classification criteria are not met

Safety Data Sheet according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

Potential Adverse human health effects and : Based on available data, the classification criteria are not met. symptoms

Toxic to aquatic life. 0.199 mg/l (96 h; Pisces)			
·			
·			
0.199 mg/l (96 h; Pisces)			
0.199 mg/l (96 h; Pisces)			
0.48 mg/l (48 h; Daphnia magna; GLP)			
> 0.4 mg/l (72 h; Scenedesmus subspicatus; GLP)			
0.363 mg/l (Algae; Chronic)			
2.2. Persistence and degradability P150-32D PAG Refrigeration Lubricant 150 + U/V Dye			
Persistence and degradability Not established.			
c o-tricresyl phosphate>95% (1330-78-5)			
Readily biodegradable in water.			
Not readily biodegradable in water. Biodegradable in the soil. Adsorbs into the soil. Low			
potential for mobility in soil. Photooxidation in the air.			
0.51 g O ² /g substance			
2.27 g O ² /g substance			
2.977 g O ² /g substance			
0.17 % ThOD			
J/V Dye			
Not established.			
c o-tricresyl phosphate>95% (1330-78-5)			
5.11 (Experimental value)			
230 - 2500 (56 days; Cyprinus carpio)			
5.1 (Experimental value)			
Potential for bioaccumulation ($500 \le BCF \le 5000$).			
May be harmful to plant growth, blooming and fruit formation.			
Avoid release to the environment.			
Dispose in a safe manner in accordance with local/national regulations.			
Avoid release to the environment.			
N			
No supplementary information available			
No supplementary information available.			

Safety Data Sheet

according to Federal Register / Vol. 77, No. 58 / Monday, March 26, 2012 / Rules and Regulations

SECTION 15: Regulatory informat	ion
15.1. US Federal regulations	
No additional information available	
15.2. International regulations	
CANADA	
P150-32D PAG Refrigeration Lubricant 1	50 + U/V Dye
WHMIS Classification	Class D Division 2 Subdivision B - Toxic material causing other toxic effects

Classification according to Regulation (EC) No. 1272/2008 [CLP]

STOT SE 2 H371 Aquatic Chronic 3 H412

Full text of H-phrases: see section 16

Classification according to Directive 67/548/EEC or 1999/45/EC

15.2.2. National regulations

No additional information available

15.3. US State regulations


P150-32D PAG Refrigeration Lubricant 150 + U/V Dye()					
U.S California - Proposition 65 - Carcinogens List		No			
U.S California - Proposition 65 - Developmental Toxicity		No			
U.S California - Proposition 65 - Reproductive Toxicity - Female		No			
U.S California - Proposition 65 - Reproductive Toxicity - Male		No			
tricresyl phosphates, mix	tricresyl phosphates, mixture of isomers, conc o-tricresyl phosphate>95% (1330-78-5)				
U.S California - Proposition 65 - Carcinogens List	U.S California - Proposition 65 - Developmental Toxicity	U.S California - Proposition 65 - Reproductive Toxicity - Female	U.S California - Proposition 65 - Reproductive Toxicity - Male	No significance risk level (NSRL)	
No	No	No	No		
2,6-di-tert-butyl-p-cresol ((128-37-0)				
U.S California - Proposition 65 - Carcinogens List	U.S California - Proposition 65 - Developmental Toxicity	U.S California - Proposition 65 - Reproductive Toxicity - Female	U.S California - Proposition 65 - Reproductive Toxicity - Male	No significance risk level (NSRL)	
No	No	No	No		

SECTION 16: Other information

NFPA health hazard

NFPA fire hazard NFPA reactivity

- : 1 Exposure could cause irritation but only minor residual injury even if no treatment is given.
- : 1 Must be preheated before ignition can occur.
- : 0 Normally stable, even under fire exposure conditions, and are not reactive with water.



SDS US (GHS HazCom 2012) - TSI

This information is furnished without warranty, expressed or implied, except that is accurate to the best knowledge of Tire Seal, Inc. The data on this sheet related only to the specific material designed herein. Tire Seal, Inc. assumes no legal responsibility for the use or reliance upon these data.